


LIMA\_07\_SV\_14\_CRUSH\_6K

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\LIMA\_07\_SV\_14\_CRUSH\_6K\LIMA\_07\_SV\_14\_CRUSH\_6K050.rdf  
 Task file: C:\CamsizerXT\CAMSYS\LIMA\_07\_SV\_14\_CRUSH\_6K.afg  
 Time: 5/18/2015 , 12:25 , duration 28 min 53 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 117102360 , CCD-Z = 914412  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.933	0.936	0.778	2
#50	#40	0.0	100.0	0.635	0.716	0.720	43
#60	#50	0.3	100.0	0.868	0.867	0.784	3596
#70	#60	5.6	99.7	0.923	0.904	0.791	101401
#140	#70	80.1	94.1	0.919	0.908	0.759	4863092
PAN	#140	14.0	14.0	0.864	0.900	0.698	212075348



Mean value SPHT3 = 0.906  
 Mean value Symm3 = 0.906  
 Mean value b/l3 = 0.740  
 Mean value RDNS\_C3 = 0.562  
 Mean value SPHT\_K3 = 0.687

User