


LIMA\_07\_SV\_14\_PRECRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\LIMA\_07\_SV\_14\_PRECRUSH\LIMA\_07\_SV\_14\_PRECRUSH043.rdf  
 Task file: C:\CamsizerXT\CAMSYS\LIMA\_07\_SV\_14\_PRECRUSH.afg  
 Time: 4/16/2015, 15:55, duration 11 min 26 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 3959217, CCD-Z = 61161  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		5.4	100.0	0.756	0.885	0.692	322
#20	#16	6.1	94.6	0.761	0.881	0.678	1027
#30	#20	6.0	88.5	0.787	0.882	0.698	2835
#40	#30	5.1	82.5	0.811	0.877	0.719	7384
#50	#40	8.7	77.4	0.863	0.885	0.746	38454
#60	#50	7.9	68.7	0.892	0.893	0.751	73376
#70	#60	10.5	60.8	0.910	0.900	0.756	159558
#140	#70	48.7	50.3	0.912	0.910	0.749	2431046
PAN	#140	1.6	1.6	0.893	0.931	0.706	8941263



Mean value SPHT3 = 0.870  
 Mean value Symm3 = 0.898  
 Mean value b/l3 = 0.723  
 Mean value RDNS\_C3 = 0.443  
 Mean value SPHT\_K3 = 0.654

User