


LIMA_08_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_08_SV_14_CRUSH_6K\LIMA_08_SV_14_CRUSH_6K046.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_08_SV_14_CRUSH_6K.afg
 Time: 5/15/2015, 15:12, duration 24 min 19 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 66062647, CCD-Z = 377087
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.688	0.747	0.731	131
#60	#50	0.9	100.0	0.879	0.874	0.780	7288
#70	#60	9.8	99.1	0.920	0.902	0.781	118277
#140	#70	77.6	89.3	0.913	0.905	0.748	2926636
PAN	#140	11.7	11.7	0.845	0.891	0.682	96245929



Characteristics

Q3 [%]	x [μm]
10.0	98.7
50.0	159.3
90.0	213.4
SPAN3 = 0.720	
U3 = 1.728	
Mv3(x) = 156.7 μm	
Sigma3(x) = 47.0 μm	

Mean value SPHT3 = 0.900
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.731
 Mean value RDNS_C3 = 0.490
 Mean value SPHT_K3 = 0.668

User