


LIMA_08_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_08_SV_14_PRECRUSH\LIMA_08_SV_14_PRECRUSH033.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_08_SV_14_PRECRUSH.afg
 Time: 5/13/2015 , 13:29 , duration 11 min 2 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 2533216 , CCD-Z = 49961
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		10.7	100.0	0.739	0.884	0.701	361
#20	#16	5.8	89.3	0.775	0.885	0.694	710
#30	#20	5.3	83.5	0.789	0.879	0.711	1851
#40	#30	5.6	78.2	0.814	0.873	0.721	5640
#50	#40	10.6	72.6	0.873	0.886	0.749	34041
#60	#50	11.7	62.0	0.906	0.899	0.754	75575
#70	#60	12.8	50.3	0.914	0.903	0.749	133573
#140	#70	36.3	37.5	0.908	0.908	0.737	1166354
PAN	#140	1.2	1.2	0.876	0.926	0.697	5333904



Characteristics

Q3 [%]	x [μm]
10.0	142.9
50.0	248.9
90.0	1217.1
SPAN3 =	4.315
U3 =	2.023
Mv3(x) =	466.7 μm
Sigma3(x) =	511.1 μm

Mean value SPHT3 = 0.862
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.422
 Mean value SPHT_K3 = 0.646

User