


LIMA_10_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_10_SV_14_CRUSH_6K\LIMA_10_SV_14_CRUSH_6K045.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_10_SV_14_CRUSH_6K.afg
 Time: 5/15/2015 , 14:42 , duration 25 min 51 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 79131658 , CCD-Z = 655526
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.659	0.734	0.732	97
#60	#50	0.6	100.0	0.867	0.867	0.782	4583
#70	#60	8.3	99.4	0.920	0.902	0.790	99812
#140	#70	78.7	91.1	0.918	0.908	0.759	2942076
PAN	#140	12.4	12.4	0.870	0.903	0.706	124827807



Mean value SPHT3 = 0.907
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.743
 Mean value RDNS_C3 = 0.563
 Mean value SPHT_K3 = 0.695

User