


LIMA_11_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_11_SV_14_CRUSH_6K\LIMA_11_SV_14_CRUSH_6K062.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_11_SV_14_CRUSH_6K.afg
 Time: 5/19/2015, 11:13, duration 20 min 56 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 33942525, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.699	0.758	0.732	98
#60	#50	1.0	100.0	0.883	0.874	0.779	5828
#70	#60	9.6	99.0	0.920	0.901	0.779	93364
#140	#70	77.4	89.4	0.929	0.905	0.753	2321933
PAN	#140	12.0	12.0	0.931	0.892	0.708	31521302



Characteristics

Q3 [%]	x [μm]
10.0	95.7
50.0	160.9
90.0	213.2
SPAN3 =	0.731
U3 =	1.792
Mv3(x) =	156.8 μm
Sigma3(x) =	48.3 μm

Mean value SPHT3 = 0.922
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.743
 Mean value RDNS_C3 = 0.461
 Mean value SPHT_K3 = 0.695

User