


LIMA_1_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_1_SV_14_PRECRUSH\LIMA_1_SV_14_PRECRUSH049.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_1_SV_14_PRECRUSH.afg
 Time: 5/21/2015, 16:00, duration 9 min 32 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3111471, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.2	100.0	0.744	0.877	0.767	43
#30	#20	2.5	99.8	0.773	0.876	0.745	1122
#40	#30	4.1	97.3	0.799	0.869	0.745	4940
#50	#40	9.1	93.2	0.850	0.872	0.751	32855
#60	#50	12.5	84.1	0.893	0.888	0.755	91148
#70	#60	17.0	71.6	0.906	0.896	0.747	199354
#140	#70	52.9	54.6	0.917	0.900	0.731	1900983
PAN	#140	1.7	1.7	0.919	0.898	0.690	881026



Characteristics

Q3 [%]	x [μm]
10.0	135.0
50.0	203.6
90.0	357.5
SPAN3 = 1.093	
U3 = 1.650	
Mv3(x) = 233.8 μm	
Sigma3(x) = 118.8 μm	

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.892
 Mean value b/l3 = 0.724
 Mean value RDNS_C3 = 0.398
 Mean value SPHT_K3 = 0.658

User