


ML_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ML_02_PRECRUSH\ML_02_PRECRUSH212.rdf
 Task file: C:\CamsizerXT\CAMSYS\ML_02_PRECRUSH.afg
 Time: 6/29/2015 , 16:51 , duration 7 min 3 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 1979868 , CCD-Z = 29530
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		3.8	100.0	0.869	0.905	0.736	224
#20	#16	10.5	96.2	0.872	0.898	0.739	2065
#30	#20	23.7	85.7	0.888	0.903	0.739	11958
#40	#30	23.4	62.0	0.893	0.904	0.728	30889
#50	#40	16.8	38.6	0.899	0.904	0.726	64125
#60	#50	7.3	21.8	0.903	0.904	0.723	59900
#70	#60	5.1	14.5	0.906	0.905	0.717	71399
#140	#70	8.7	9.4	0.897	0.905	0.706	376021
PAN	#140	0.7	0.7	0.848	0.917	0.665	6590891



Characteristics

Q3 [%]	x [μm]
10.0	216.4
50.0	511.5
90.0	935.8
SPAN3 =	1.406
U3 =	2.702
Mv3(x) =	557.5 μm
Sigma3(x) =	321.1 μm

Mean value SPHT3 = 0.885
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.713
 Mean value RDNS_C3 = 0.550
 Mean value SPHT_K3 = 0.620

User