


RING_1_SV_14_SHR_RND

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\RING_1_SV_14_SHR_RND\RING_1_SV_14_SHR_RND050.rdf
 Task file: C:\CamsizerXT\CAMSYS\RING_1_SV_14_SHR_RND.afg
 Time: 3/3/2015 , 14:40 , duration 5 min 35 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 2093075 , CCD-Z = 43855
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.1	100.0	0.624	0.700	0.701	228
#60	#50	1.0	99.9	0.813	0.827	0.741	4099
#70	#60	11.1	98.9	0.898	0.888	0.762	72786
#140	#70	86.6	87.8	0.911	0.907	0.740	1489298
PAN	#140	1.2	1.2	0.867	0.918	0.644	6127559



Mean value SPHT3 = 0.900
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.620
 Mean value SPHT_K3 = 0.651

User