


SGVIR_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\SGVIR_01_PRECRUSH\SGVIR_01_PRECRUSH065.rdf
 Task file: C:\CamsizerXT\CAMSYS\SGVIR_01_PRECRUSH.afg
 Time: 7/20/2015 , 14:34 , duration 18 min 10 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3507682 , CCD-Z = 23898
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		8.1	100.0	0.756	0.888	0.711	127
#20	#16	11.3	91.9	0.795	0.890	0.736	553
#30	#20	11.8	80.6	0.803	0.887	0.732	1544
#40	#30	9.5	68.8	0.830	0.887	0.736	3518
#50	#40	7.9	59.3	0.850	0.884	0.738	8510
#60	#50	3.9	51.4	0.863	0.882	0.736	9050
#70	#60	4.6	47.5	0.884	0.886	0.745	18633
#140	#70	36.3	42.9	0.887	0.898	0.723	513614
PAN	#140	6.6	6.6	0.836	0.904	0.677	4057529



Characteristics

Q3 [%]	x [μm]
10.0	118.8
50.0	280.8
90.0	1105.1
SPAN3 = 3.512	
U3 = 3.666	
Mv3(x) = 478.4 μm	
Sigma3(x) = 425.4 μm	

Mean value SPHT3 = 0.840
 Mean value Symm3 = 0.892
 Mean value b/l3 = 0.715
 Mean value RDNS_C3 = 0.363
 Mean value SPHT_K3 = 0.642

User