


SGVIR\_04\_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\SGVIR_04_PRECRUSH\SGVIR_04_PRECRUSH074.rdf
Task file:	C:\CamsizerXT\CAMSYS\SGVIR_04_PRECRUSH.afg
Time:	7/21/2015 , 11:37 , duration 16 min 1 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 6738648 , CCD-Z = 66845
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		5.3	100.0	0.778	0.892	0.711	66
#20	#16	9.7	94.7	0.789	0.883	0.699	298
#30	#20	10.9	85.0	0.798	0.882	0.696	913
#40	#30	10.7	74.1	0.830	0.886	0.717	2619
#50	#40	10.5	63.4	0.851	0.885	0.725	7347
#60	#50	5.4	52.9	0.869	0.886	0.729	8213
#70	#60	5.1	47.5	0.883	0.887	0.735	13495
#140	#70	33.9	42.4	0.891	0.898	0.723	332911
PAN	#140	8.5	8.5	0.857	0.909	0.688	16963338



Mean value SPHT3 = 0.845
Mean value Symm3 = 0.891
Mean value b/l3 = 0.704
Mean value RDNS_C3 = 0.385
Mean value SPHT_K3 = 0.611

User