


SS_02_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\SS_02_5KCRUSH\SS_02_5KCRUSH090.rdf
 Task file: C:\CamsizerXT\CAMSYS\SS_02_5KCRUSH.afg
 Time: 3/30/2016 , 12:05 , duration 26 min 57 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 36411618 , CCD-Z = 530109
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.950	0.944	0.777	10
#40	#30	0.0	100.0	0.899	0.908	0.713	12
#50	#40	0.1	100.0	0.735	0.825	0.693	31
#60	#50	0.1	99.9	0.833	0.849	0.771	596
#70	#60	1.3	99.8	0.899	0.886	0.786	13014
#140	#70	71.8	98.5	0.911	0.907	0.751	3206549
PAN	#140	26.7	26.7	0.896	0.924	0.721	70544628



Characteristics

Q3 [%]	x [μm]
10.0	82.7
50.0	125.3
90.0	175.3
SPAN3 = 0.739	
U3 = 1.614	
Mv3(x) = 127.3 μm	
Sigma3(x) = 38.9 μm	

Mean value SPHT3 = 0.901
 Mean value Symm3 = 0.909
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.663
 Mean value SPHT_K3 = 0.649

User