


VAL_01_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\VAL_01_SV_14_CRUSH_6K\VAL_01_SV_14_CRUSH_6K107.rdf
 Task file: C:\CamsizerXT\CAMSYS\VAL_01_SV_14_CRUSH_6K.afg
 Time: 6/10/2015, 9:22, duration 38 min 20 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 149231378, CCD-Z = 1246196
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.1	100.0	0.626	0.854	0.688	34
#20	#16	0.9	98.9	0.709	0.861	0.700	129
#30	#20	1.6	98.0	0.721	0.858	0.702	659
#40	#30	2.5	96.4	0.766	0.857	0.712	2836
#50	#40	4.1	93.9	0.799	0.856	0.716	12753
#60	#50	3.2	89.8	0.837	0.864	0.724	22278
#70	#60	7.1	86.6	0.886	0.886	0.752	83678
#140	#70	58.6	79.5	0.903	0.902	0.742	2403173
PAN	#140	20.9	20.9	0.867	0.901	0.715	202296603



Characteristics

Q3 [%]	x [μm]
10.0	57.3
50.0	155.8
90.0	303.5
SPAN3 =	1.580
U3 =	2.983
Mv3(x) =	196.0 μm
Sigma3(x) =	216.3 μm

Mean value SPHT3 = 0.871
 Mean value Symm3 = 0.894
 Mean value b/l3 = 0.718
 Mean value RDNS_C3 = 0.477
 Mean value SPHT_K3 = 0.642

User