


WSS_01_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_01_SV_14_PRECRUSH\WSS_01_SV_14_PRECRUSH129.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_01_SV_14_PRECRUSH.afg
 Time: 6/12/2015, 12:41, duration 7 min 1 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 7960623, CCD-Z = 122587
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		7.2	100.0	0.741	0.872	0.705	366
#20	#16	10.6	92.8	0.758	0.874	0.672	1418
#30	#20	12.2	82.2	0.785	0.872	0.692	4574
#40	#30	12.3	70.0	0.819	0.873	0.706	13206
#50	#40	15.7	57.7	0.862	0.883	0.727	51510
#60	#50	12.0	42.0	0.895	0.897	0.742	84573
#70	#60	10.5	30.0	0.907	0.903	0.741	119507
#140	#70	17.5	19.5	0.899	0.902	0.724	588714
PAN	#140	2.0	2.0	0.848	0.908	0.686	28586174



Mean value SPHT3 = 0.836
 Mean value Symm3 = 0.885
 Mean value b/l3 = 0.700
 Mean value RDNS_C3 = 0.358
 Mean value SPHT_K3 = 0.608

User