


WSS_03_SV_14_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_03_SV_14_CRUSH5K\WSS_03_SV_14_CRUSH5K070.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_03_SV_14_CRUSH5K.afg
 Time: 3/10/2015, 13:58, duration 17 min 35 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 95307951, CCD-Z = 5061
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	3.3	100.0	0.891	0.902	0.789	6003
#40	#30	30.5	96.7	0.897	0.906	0.761	116124
#50	#40	37.2	66.2	0.902	0.907	0.744	353644
#60	#50	7.7	29.0	0.889	0.900	0.710	153664
#70	#60	3.7	21.3	0.887	0.895	0.709	125650
#140	#70	6.3	17.6	0.856	0.887	0.699	792312
PAN	#140	11.3	11.3	0.764	0.874	0.629	248873874



Characteristics

Q3 [%]	x [μm]
10.0	82.8
50.0	371.1
90.0	540.1
SPAN3 = 1.232	
U3 = 4.872	
Mv3(x) = 354.2 μm	
Sigma3(x) = 153.3 μm	

Mean value SPHT3 = 0.872
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.716
 Mean value RDNS_C3 = 0.505
 Mean value SPHT_K3 = 0.636

User