


WSS_04_CRUSH5K_02

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_04_CRUSH5K_02\WSS_04_CRUSH5K_02059.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_04_CRUSH5K_02.afg
 Time: 8/11/2015 , 15:59 , duration 18 min 34 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 57128439 , CCD-Z = 658203
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	2.3	100.0	0.889	0.900	0.796	2487
#40	#30	29.0	97.7	0.899	0.906	0.768	68962
#50	#40	44.4	68.7	0.903	0.907	0.749	255163
#60	#50	8.8	24.3	0.888	0.899	0.709	103140
#70	#60	3.8	15.5	0.882	0.893	0.703	77188
#140	#70	7.1	11.7	0.861	0.886	0.673	472660
PAN	#140	4.6	4.6	0.829	0.892	0.657	99254451



Characteristics

Q3 [%]	x [μm]
10.0	191.6
50.0	371.9
90.0	522.1
SPAN3 =	0.889
U3 =	2.081
Mv3(x) =	365.9 μm
Sigma3(x) =	126.9 μm

Mean value SPHT3 = 0.888
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.561
 Mean value SPHT_K3 = 0.661

User