


WSS_05_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_05_SV_14_PRECRUSH\WSS_05_SV_14_PRECRUSH065.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_05_SV_14_PRECRUSH.afg
 Time: 3/10/2015, 8:54, duration 8 min 17 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 6118646, CCD-Z = 3004
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		6.1	100.0	0.734	0.864	0.711	530
#20	#16	8.6	93.9	0.775	0.867	0.710	2045
#30	#20	15.1	85.3	0.835	0.880	0.731	10037
#40	#30	24.0	70.2	0.877	0.895	0.736	43997
#50	#40	24.5	46.2	0.896	0.904	0.731	120047
#60	#50	8.3	21.7	0.898	0.904	0.718	86002
#70	#60	4.7	13.4	0.897	0.902	0.708	81087
#140	#70	6.6	8.7	0.870	0.894	0.682	366094
PAN	#140	2.1	2.1	0.768	0.875	0.630	8727325



Characteristics

Q3 [%]	x [μm]
10.0	223.7
50.0	446.3
90.0	998.9
SPAN3 =	1.737
U3 =	2.285
Mv3(x) =	533.9 μm
Sigma3(x) =	322.7 μm

Mean value SPHT3 = 0.852
 Mean value Symm3 = 0.890
 Mean value b/l3 = 0.708
 Mean value RDNS_C3 = 0.462
 Mean value SPHT_K3 = 0.623

User