


WSS_06_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_06_SV_14_PRECRUSH\WSS_06_SV_14_PRECRUSH068.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_06_SV_14_PRECRUSH.afg
 Time: 3/10/2015, 13:09, duration 6 min 3 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3506525, CCD-Z = 1250
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		11.8	100.0	0.775	0.878	0.713	938
#20	#16	16.3	88.2	0.822	0.886	0.726	3955
#30	#20	19.4	71.9	0.844	0.890	0.724	12397
#40	#30	16.8	52.5	0.854	0.888	0.714	29859
#50	#40	14.3	35.7	0.869	0.891	0.712	72160
#60	#50	6.4	21.4	0.880	0.894	0.710	70896
#70	#60	5.0	15.0	0.889	0.897	0.709	90163
#140	#70	9.1	10.0	0.869	0.895	0.690	507135
PAN	#140	0.9	0.9	0.788	0.882	0.624	3616659



Characteristics

Q3 [%]	x [µm]
10.0	211.8
50.0	572.2
90.0	1240.6
SPAN3 = 1.798	
U3 = 3.248	
Mv3(x) = 659.1 µm	
Sigma3(x) = 411.5 µm	

Mean value SPHT3 = 0.837
 Mean value Symm3 = 0.888
 Mean value b/l3 = 0.698
 Mean value RDNS_C3 = 0.374
 Mean value SPHT_K3 = 0.601

User