


WSS_07_SV_14_6KCRUSH_NO3

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_07_SV_14_6KCRUSH_NO3\WSS_07_SV_14_6KCRUSH_NO3045.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_07_SV_14_6KCRUSH_NO3.afg
 Time: 7/6/2015, 13:33, duration 20 min 52 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 115371240, CCD-Z = 809634
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	2.2	100.0	0.905	0.909	0.801	3691
#40	#30	25.7	97.8	0.908	0.911	0.771	93702
#50	#40	37.7	72.1	0.908	0.909	0.752	349757
#60	#50	13.7	34.4	0.903	0.906	0.733	264021
#70	#60	5.8	20.7	0.891	0.898	0.708	177236
#140	#70	8.9	14.9	0.866	0.889	0.682	937820
PAN	#140	6.0	6.0	0.832	0.894	0.661	198033990



Characteristics

Q3 [%]	x [μm]
10.0	159.4
50.0	348.7
90.0	517.4
SPAN3 =	1.027
U3 =	2.392
Mv3(x) =	345.7 μm
Sigma3(x) =	134.0 μm

Mean value SPHT3 = 0.893
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.598
 Mean value SPHT_K3 = 0.659

User