


WSS_07_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_07_SV_14_PRECRUSH\WSS_07_SV_14_PRECRUSH049.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_07_SV_14_PRECRUSH.afg
 Time: 4/2/2015 , 15:30 , duration 7 min 3 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3941193 , CCD-Z = 4
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.9	100.0	0.797	0.879	0.766	161
#20	#16	4.7	98.1	0.830	0.887	0.754	1124
#30	#20	16.3	93.4	0.880	0.902	0.760	10678
#40	#30	28.2	77.1	0.898	0.906	0.750	48619
#50	#40	28.6	48.9	0.908	0.910	0.740	132282
#60	#50	9.5	20.3	0.911	0.910	0.729	95200
#70	#60	5.5	10.8	0.914	0.911	0.726	89145
#140	#70	5.2	5.3	0.914	0.908	0.715	194025
PAN	#140	0.1	0.1	0.901	0.893	0.688	6034



Characteristics

Q3 [%]	x [μm]
10.0	245.3
50.0	430.0
90.0	762.9
SPAN3 =	1.204
U3 =	1.964
Mv3(x) =	481.0 μm
Sigma3(x) =	235.2 μm

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.731
 Mean value RDNS_C3 = 0.594
 Mean value SPHT_K3 = 0.667

User