


WSS_2_SV_14_5KCRUSH

Company:
User:
Result file: C:\CamsizerXT\CAMDAT\WSS_2_SV_14_5KCRUSH\WSS_2_SV_14_5KCRUSH075.rdf
Task file: C:\CamsizerXT\CAMSYS\WSS_2_SV_14_5KCRUSH.afg
Time: 3/10/2015, 15:40, duration 18 min 1 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
No. of particles: CCD-B = 27223757, CCD-Z = 192
Velocity adaption: no
Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	5.1	100.0	0.889	0.897	0.785	9057
#40	#30	46.3	94.9	0.903	0.908	0.757	167909
#50	#40	39.7	48.6	0.900	0.906	0.732	339246
#60	#50	4.8	8.9	0.876	0.896	0.678	85967
#70	#60	1.7	4.1	0.869	0.889	0.676	52004
#140	#70	2.2	2.4	0.869	0.885	0.671	198458
PAN	#140	0.2	0.2	0.872	0.882	0.661	123088



Characteristics

Q3 [%]	x [μm]
10.0	306.8
50.0	428.8
90.0	567.4
SPAN3 =	0.608
U3 =	1.488
Mv3(x) =	431.4 μm
Sigma3(x) =	103.6 μm

Mean value SPHT3 = 0.893
Mean value Symm3 = 0.905
Mean value b/l3 = 0.728
Mean value RDNS_C3 = 0.590
Mean value SPHT_K3 = 0.659

User