


WSS_3_SANDR50

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_3_SANDR50\WSS_3_SANDR50059.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_3_SANDR50.afg
 Time: 3/9/2015 , 15:30 , duration 3 min 41 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 928720 , CCD-Z = 3478
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.1	100.0	0.536	0.648	0.678	42
#40	#30	18.5	99.9	0.880	0.889	0.761	21861
#50	#40	74.7	81.4	0.896	0.904	0.727	162618
#60	#50	6.1	6.7	0.865	0.903	0.625	23210
#70	#60	0.5	0.6	0.802	0.893	0.519	2589
#140	#70	0.1	0.1	0.700	0.870	0.420	571
PAN	#140	0.0	0.0	0.786	0.871	0.646	1891959



Mean value SPHT3 = 0.883
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.711
 Mean value RDNS_C3 = 0.575
 Mean value SPHT_K3 = 0.621

User