


WSS_5_SANDR50

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\WSS_5_SANDR50\WSS_5_SANDR50057.rdf
 Task file: C:\CamsizerXT\CAMSYS\WSS_5_SANDR50.afg
 Time: 3/9/2015 , 14:49 , duration 3 min 44 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 818528 , CCD-Z = 4398
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.640	0.701	0.727	20
#40	#30	16.8	100.0	0.887	0.891	0.769	20178
#50	#40	75.9	83.2	0.902	0.906	0.735	170373
#60	#50	6.5	7.3	0.867	0.904	0.628	25111
#70	#60	0.7	0.8	0.796	0.890	0.514	3292
#140	#70	0.1	0.1	0.699	0.862	0.422	880
PAN	#140	0.0	0.0	0.805	0.878	0.645	2373506



Mean value SPHT3 = 0.890
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.718
 Mean value RDNS_C3 = 0.585
 Mean value SPHT_K3 = 0.636

User