


C80_01_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C80_01_5KCRUSH\C80_01_5KCRUSH165.rdf
 Task file: C:\CamsizerXT\CAMSYS\C80_01_5KCRUSH.afg
 Time: 12/22/2015 , 11:55 , duration 23 min 22 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 31335350 , CCD-Z = 591055
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.670	0.741	0.729	279
#60	#50	0.9	100.0	0.858	0.855	0.770	9386
#70	#60	10.0	99.1	0.917	0.897	0.781	163355
#140	#70	85.2	89.1	0.919	0.911	0.739	3587797
PAN	#140	3.9	3.9	0.871	0.915	0.697	58989495



Characteristics

Q3 [%]	x [μm]
10.0	126.9
50.0	172.9
90.0	213.6
SPAN3 =	0.501
U3 =	1.426
Mv3(x) =	170.8 μm
Sigma3(x) =	36.4 μm

Mean value SPHT3 = 0.910
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.665
 Mean value SPHT_K3 = 0.649

User